

Bandar Imam Petrochemical Company

# SBR 1500

Property	Test Method	Value	Unit
Volatile Matter	ASTM D-1416	0.75 max	%wt
Ash	ASTM D-1416	1.5 max	%wt
Organic Acid	ASTM D-1416	5-7.25	%wt
Soap	ASTM D-1416	0.5 max	%wt
Bound Styrene	ASTM D-1416	22.5-24.5	%wt
Raw Viscosity (ML 1+4 @ 100°C)	ASTM D-1646	46-58	-
Compound Viscosity (ML 1+4 @ 100°C)	ASTM D-1646	84 max	-
tensile Strenght (35 Minutes Cure)	ASTM D-412	250 min	kg/cm2
Ultimate Elogation (35 Minutes Cure)	ASTM D-412	470 min	%
300% Modulus (35 Minutes Cure)	ASTM D-412	119-159	kg/cm2

## APPLICATION

tires, tube, cable, mechanical industries



+77017111544  
+96893915661



Email: [info@atlaspetro.com](mailto:info@atlaspetro.com)



[www.atlaspetro.com](http://www.atlaspetro.com)