

Khuzestan Petrochemical Company

# Epiran-01 X-75 LC

## SOID EPOXY RESIN IN MIXED XYLENE

PROPERTY	TEST METHOD	UNIT	GUARANTEE VALUES
Appearance	Visual	Visual	Clear Light Yellow Liquid
Epoxy Equivalent	ASTM D1652	g/eq	434-555
Epoxy Value	ASTM D1652	mol/100gr	0.18-0.23
Color	ASTM 1209 (APHA)	Pt-Co (APHA)	Max. 40
Viscosity	ASTM D2983	Mpas	6000-12000
Hydrolysable Chlorine	ASTM 1726	% wt	Max. 0.1
%Non-Volatile	DIN EN ISO 3251	% wt	74-76

## APPLICATION

is used for cold cured varnished, solvent based 2-pack coatings for metals, as modifier in stoving enamel based on acrylics, alkyd-melamin resin systems and hot cured adhesives manufacture



+77017111544  
+96893915661



Email: [info@atlaspetro.com](mailto:info@atlaspetro.com)



[www.atlaspetro.com](http://www.atlaspetro.com)