

Khuzestan Petrochemical Company

Epiran-05 (SPL)

LIQUID EPOXY RESIN SPECIAL

PROPERTY	TEST METHOD	UNIT	GUARANTEE VALUES
Appearance	Visual	Visual	Clear Light Yellow Liquid
Epoxy Equivalent	ASTM D1652	g/eq	192-204
Epoxy Value	ASTM D1652	mol/100gr	0.49-0.521
Color	ASTM 1209 (APHA)	Pt-Co (APHA)	Max.100
Viscosity at 25 °C	ASTM D2983	Mpas	15000-20000
Hydrolysable Chlorine	ASTM 1726	% wt	Max. 0.2
Non-Volatile	DIN EN ISO 3251	% wt	Min 99

APPLICATION

for civil Engineering Coating, flooring, Adhesives, Mortars, Grouts, Industrial Maintenance & Marine Coating



+77017111544
+96893915661



Email: info@atlaspetro.com



www.atlaspetro.com