

Khouzestan Petrochemical Company

Epiran-06 (SPL)

LIQUID EPOXY RESIN SPECIAL

PROPERTY	TEST METHOD	UNIT	GUARANTEE VALUES
Appearance	Visual	Visual	Clear Light Yellow Liquid
Epoxy Equivalent	ASTM D1652	g/eq	185-192
Epoxy Value	ASTM D1652	mol/100gr	0.52-0.54
Color	ASTM 1209	Pt-Co (APHA)	Max. 50
Viscosity at 25 °C	ASTM D2983	Mpas	10000-14000
Hydrolysable Chlorine	ASTM 1726	% wt	Max. 0.1
Non-Volatile	DIN EN ISO 3251	% wt	Min 99.3

APPLICATION

adhesives, casting, tooling, civil eng. Composites, Automotive, can and coatings, marine and protective coating, electrical and electronic use . Potting and encapsulation



+77017111544
+96893915661



Email: info@atlaspetro.com



www.atlaspetro.com