

Khuzestan Petrochemical Company

# Epiran-06

## LIQUID EPOXY RESIN

PROPERTY	TEST METHOD	UNIT	GUARANTEE VALUES
Appearance	Visual	Visual	Clear Light Yellow Liquid
Epoxy Equivalent	ASTM D1652	g/eq	185-196
Epoxy Value	ASTM D1652	mol/100gr	0.51-0.54
Color	ASTM 1209 (APHA)	Pt-Co (APHA)	Max. 100
Viscosity	ASTM D2983	Mpas	<15000
Hydrolysable Chlorine	ASTM 1726	% wt	Max. 0.2
Non-Volatile	DIN EN ISO 3251	% wt	Min 99

## APPLICATION

adhesives, casting, tooling, civil eng. Composites, Automotive, can and coatings, marine and protective coating, electrical and electronic use . Potting and encapsulation



+77017111544  
+96893915661



Email: [info@atlaspetro.com](mailto:info@atlaspetro.com)



[www.atlaspetro.com](http://www.atlaspetro.com)