

Khouzestan Petrochemical Company

Epiran-11

SOLID EPOXY RESIN

PROPERTY	TEST METHOD	UNIT	GUARANTEE VALUES
Appearance	Visual	Visual	Clear Light Yellow Flakes
Epoxy Equivalent	ASTM D1652	g/eq	715-870
Epoxy Value	ASTM D1652	mol/100gr	0.115-0.14
Color	ASTM 1209 (APHA)	Pt-Co (APHA)	Max.100
Softening Point	DIN 52011	°C	84-98
Hydrolysable Chlorine	ASTM 1726	% wt	Max. 0.1

APPLICATION

is used for hot cured varnishes, Powder coating, Adhesives manufacture



+77017111544
+96893915661



Email: info@atlaspetro.com



www.atlaspetro.com