

Khuzestan Petrochemical Company

Epiran-12

SOLID EPOXY RESIN

PROPERTY	TEST METHOD	UNIT	GUARANTEE VALUES
Appearance	Visual	Visual	Clear, Light Yellow Flakes
Epoxy Equivalent	ASTM D1652	g/eq	800-1000
Epoxy Value	ASTM D1652	mol/100gr	0.1-0.125
Color	ASTM 1209 (APHA)	Pt-Co (APHA)	Max.100
Softening Point	DIN 52011	°C	93-105
Hydrolisable Chlorine	ASTM 1726	% wt	Max. 0.2

APPLICATION

is used for cold cured varnishes, Powder coating, Electrical Insulation and Epoxy Surface Coating manufacture



+77017111544
+96893915661



Email: info@atlaspetro.com



www.atlaspetro.com