

Styrene Monomer

PROPERTY	UNIT	TEST METHOD	ACCEPTANCE CRITERIA*
PURITY	%WT	ASTM D-5135	MIN 99.7
COLOR(PT-CO)SCALE	-	ASTM D-1209	MAX 10
POLYMERS	PPM wt	ASTM D-2121	MAX 10
INHIBITOR(AS TBC)	PPM wt	ASTM D-4590	MAX 15**
ALDEHYDES(AS BENZALDEHYDE)	PPM wt	ASTM D-2119	MAX 100
PEROXIDE(AS H2O2)	PPM wt	ASTM D-2340	MAX 50
TOTAL SULFUR	PPM wt	ASTM D-3120	MAX 5
ETHYLBENZENE	PPM wt	ASTM D-5453	MAX 1000
WATER	PPM wt	UOP-481	MAX 150

*Acceptance Criteria refers to the parameters which are tested regularly. These items are guaranteed figures.



+77017111544
+96893915661



Email: info@atlaspetro.com



www.atlaspetro.com